

COSTAR EPOXY CONCRETE REPAIR MORTAR

Costar Shrink-Free Epoxy Concrete Repair

Description

COSTAR EPOXY CONCRETE REPAIR MORTAR is a solvent-free repair mortar with low viscosity. It is a two-component solution, which consists of rapid curing resin based mortar and primer for coating. And appropriate for different ranges of civil works where highly penetrating material is required. It is non-sag property makes it suitable for vertical repairs. Suitable for the repair and filling of cracks up to 6mm wide in a construction works, varying from concrete, bricks, stucco, stone, concrete blocks, tile and other substrates, likewise, provides long-lasting repair for worn-out concrete. For aesthetic finishes, it can be painted or coated to achieve the desired appearance after tack free (approximately 3 hours).

Features

- Stands up to heavy traffic and many chemicals
- Does not shrink or crack
- High tensile strength
- For repairing eroded or damaged concrete, bay edges and broken steps
- Easy all-in-1 packaging
- For interior and exterior use

Instructions for Use

■ Surface Preparation

Concrete and stone surfaces should be dry and free from previous coatings, contaminants and loose material. Very smooth concrete or concrete with soft laitance should be etched. Grease or oil should be removed and the area thoroughly washed off and allowed to become completely dry.

■ Mixing

The pack includes a granular resinous material (Part A-Resin) and curing agent (Part B-Hardener).

Mix the granular resinous material with the curing agent on a board. It is important that mixing should be carried out very thoroughly.

Product Preparation

■ Application & Thinning

Trowel vigorously over the prepared surface. Final leveling should be carried out with a steel float. To prevent 'drag' it is advisable to wipe the blade of the tool frequently with a rag moistened (but not saturated) with white spirit. The working life of the mixed product is half to one hour depending on temperature. If the product is used past its working life, trowelling will become difficult and adhesion reduced.



COSTAR EPOXY CONCRETE REPAIR MORTAR

Costar Shrink-Free Epoxy Concrete Repair

Technical Data

Density	1.7kg/l
Solid Content in Volume	1
Solid Content in Weight	1
Compressive Strength	55.2MN/N ²
Tensile Strength	15.4MN/N ²

Packaging

20Kg

Shelf Life

Protect from freezing and contamination. Shelf life in unopened, original containers is 18 months, when stored at 40°F to 90°F unopened in dry storage

Precaution

Do not thin with solvents, as this will prevent cure. Do not use for repairing cracks that are subject to movement until the cause has been addressed. Do not apply in areas where service temperatures may reach 140°F (60°C) or higher. Do not attempt to force material through a mixing nozzle that contains hardened material; material may splatter. If a leak should develop, discontinue use immediately. Proceed with new cartridge and nozzle.

Handling Precaution

- Do not apply more than the recommended amount.
- Do not leave puddles. If puddles form on textured surfaces, use a brush to remove them.
- When used as a curing compound, do not apply to finished concrete surface too quickly. Under typical conditions, the proper application time will be 4-6 hours after placing.
- When used as a curing compound in hot, windy weather, the proper application time will be reduced to as little as 2-3 hours after placing.
- Wait at least 10-12 hours in cool weather. Apply after finishing and when surface water has been reabsorbed.
- Do not apply if rain, heavy dew or temperatures below 50°F (10°C) are expected within 24 hours. Keep from freezing during storage.
- Do not cover surfaces treated with COSTAR EPOXY CONCRETE REPAIR for at least 24 hours after application.
- Avoid Contact with eyes and skin
- If skin contact occurs, wash skin thoroughly
- Wear Protective gloves and eye protection during work
- If In eyes, hold eyes open, flood with warm water and seek medical attention immediately



COSTAR EPOXY CONCRETE REPAIR MORTAR

Costar Shrink-Free Epoxy Concrete Repair

Limited Warranty

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use away.



Call Us:
+9254348314

E-mail Us
Info@costarchem.com

Office Address:
5041 Mountaire Area, Antioch, California, USA